



PDS No: SRP 002/18
Date: 12/9/18
Rev: 2

SISSONS ROOFCOTE

PRODUCT DESCRIPTION: A tough flexible paint specially formulated to withstand the severity of wind, rain and sun on all types or roofs.

RECOMMENDED TYPICAL USES: Suitable for the general decoration and preservation of interior and exterior metallic surfaces.

ADVANTAGES:

1. Ease of application
2. Good adhesion on metals
3. Resists fungus and mildew.
4. Flexible enough to withstand normal expansion and contraction

DIRECTIONS FOR USE:

New Galvanize Sheets:

Surface must be solvent wiped first to remove oil, grease etc, then coated with one coat of Sissons One-Pack Etch Primer. This primer must be recoated the same day and not allowed to stand overnight. Sissons Roofcote can be applied directly to the Etch Primer, one or two coats, however for a very long-lasting finish a coat of Sissons Zinc Chromate Primer can be applied before top coating with Roofcote.

Weathered Galvanize:

Weathered galvanized surfaces covered with "White Rust" must be thoroughly washed, preferably by high pressure before applying one coat of Sissons Zinc Chromate Primer followed by one or two coats of Roofcote.

An exposed roof may appear 'clean', however there is an accumulation of dirt and white rust that must be removed before painting.

New Galvanize Sheets:

Surface must be solvent wiped first to remove oil, grease etc, then coated with one coat of Sissons One-Pack Etch Primer. This primer must be recoated the same day and not allowed to stand overnight. Sissons Roofcote can be applied directly to the Etch Primer, one or two coats, however for a very long-lasting finish a coat of Sissons Zinc Chromate Primer can be applied before top coating with Roofcote.

Weathered Galvanize:

Weathered galvanized surfaces covered with "White Rust" must be thoroughly washed, preferably by high pressure before applying one coat of Sissons Zinc Chromate Primer followed by one or two coats of Roofcote.

An exposed roof may appear 'clean', however there is an accumulation of dirt and white rust that must be removed before painting.

TECHNICAL DATA

PRODUCT REF: SRP SERIES

GENERIC TYPE: Based on a long oil soya alkyd

COLOUR: Green, Aluminum and Red

PACK SIZES: ¼ US & 1 US Gallon.

SPREADING RATE: 350-375 sq ft /US Gallon depending on surface condition.

FLASH POINT: 113 °F or 45 °C

DRYING TIMES:

To Touch 4 to 6 hours

Re-coat – 18 hours

Hard Dry – 24 hours

APPLICATION METHODS: Brush, Roller or spray application 1-1 ½ pt of Sissons Paints Thinners per 1 US Gallon may be used.

THINNER/CLEAN UP: Sissons Paint Thinners.

SOLIDS BY WEIGHT: 69.43%

SOLIDS BY VOLUME: 58.87%

V.O.C.: 348.32 gm / litre

These recommendation and data are offered in good faith, but without guarantee or warranty, as conditions and methods of use of our products are beyond our control

ANSA Coatings Limited