



PDS No: SFP 001/18  
Date: 12/9/18  
Rev:2

---

## SISSONS FLOOR PAINT

**PRODUCT DESCRIPTION:** An alkyd-based floor paint with an attractive gloss finish.

**RECOMMENDED TYPICAL USES:**

Ideal for factory warehouse and all non-porous floor surfaces.

**ADVANTAGES:**

1. Quick Drying.
2. Suitable on stone, concrete and wooden floors.
3. Hard wearing. Resistant to foot and light vehicular traffic.
4. Resistant to oil and grease.

**DIRECTIONS FOR USE:** Surfaces should be clean, dry and must be free from grease or wax polish, otherwise the film will remain sticky and not harden

**New Concrete:**

This should be left until thoroughly dry and hardened before painting. Smooth or trowel clean surfaces must be acid etched or alternatively abraded before a thinned down primer coat of floor paint is applied. Thin paint in the ratio of 3 parts to 1-part Sissons Paint Thinners. Apply this thinned paint by brush ensuring that the paint is applied lightly and worked into the concrete surface to promote proper penetration and good adhesion. Allow 6 – 8 hours drying before applying a second unthinned coat.

**Previously Painted Surfaces:**

Surfaces must be free from old flaking paint, dust, oil & wax. This is best achieved by scraping and wire brushing. If wax or oil is present degrease by wiping with Sissons Paint Thinners. Thin paint as above and apply this coat as a sealer. Follow with a second unthinned coat, allowing overnight drying between coats.

**TECHNICAL DATA**

**PRODUCT REF:** SFP SERIES

**GENERIC TYPE:** Combination of long and medium soybean oil

**COLOUR:** Available in three standard colours: red, grey, green

**PACK SIZES:** Available in ¼ US & 1 US Gallon.

**SPREADING RATE:** 350-375 sq. ft. /US Gallon.

**FLASH POINT:** 113 °F or 45 °C

**DRYING TIMES:**

Touch Dry- 2 to 4 hours

Recoat – 8 hours

Hard Dry – 12 hours

**APPLICATION METHODS:** Brush or spray

**THINNER/CLEAN UP:** Sissons Paints Thinners

**SOLIDS BY WEIGHT:** 48.10%

**SOLIDS BY VOLUME:** 41.43%

**V.O.C.:** 408.04 gm/litre

These recommendation and data are offered in good faith, but without guarantee or warranty, as conditions and methods of use of our products are beyond our control

**ANSA Coatings Limited**